

A. ITEM - AGGREGATE BASE (Class 1 or 2)

The Aggregate Base shall be Class **, and shall be as specified in Section 303 of the Standard Specifications.

The estimated haul distance for the Aggregate Base is * miles.

Please refer to the DESIGNER NOTES and consult with the Pavement Design Engineer prior to using either Items B or C below.

B. ITEM - AGGREGATE BASE (Class 1 or 2)

The Aggregate Base may consist of one or more of the following:

1. The Aggregate Base shall be Class ** and shall be as specified in Section 303 of the Standard Specifications.
2. Aggregate Base consisting of 1 part (by volume) new AB Class ** as specified in Section 303 of the Standard Specifications, and 1 part (by volume) milled AC, 100% passing the 1 ½" sieve. The milled AC shall contain no underlying base or subgrade materials. The mixture of AB and milled AC shall be thoroughly blended to the satisfaction of the Engineer prior to compaction.
3. Aggregate Base consisting of 1 part (by volume) new AB Class ** as specified in Section 303 of the Standard Specifications, and 1 part (by volume) crushed AC, 100% passing the 1 ½" sieve. The crushed AC shall contain no underlying base or subgrade materials. Prior to crushing, all material passing the ½" sieve shall be removed. The removed material shall not be used for aggregate base. The mixture of AB and crushed AC shall be thoroughly blended to the satisfaction of the Engineer prior to compaction.

The estimated haul distance for the Aggregate Base is * miles.

C. ITEM - AGGREGATE BASE (Class 1 or 2)

The Aggregate Base may consist of one or both of the following:

1. The Aggregate Base shall be Class ** and shall be as specified in Section 303 of the Standard Specifications.
2. The Aggregate Base shall be Class ** and shall be as specified in Section 303 of the Standard Specifications, and Contracts and Specifications Stored Spec. "303SALV."

The estimated haul distance for the Aggregate Base is * miles.

DESIGNER:

* To be supplied by the Geotechnical Site Supervisor.

** List AB type (Class 1 or 2) whichever is applicable. If Class 3 is used include gradation and plasticity index information. (See Item # 303d).

Items B or C shall be used when milled or crushed AC is being considered for use in aggregate base. In addition to milled or crushed AC, if pulverized AC or crushed PCCP is being considered for use in aggregate base, Item C must be used.

When the estimated quantity of aggregate subbase is approximately 1,000 CY or less, use Item B. Prior to using Item B, consult with the Pavement Design Engineer.

When the estimated quantity of aggregate subbase is greater than 1,000 CY, use Item C. Prior to using Item C, consult with the Pavement Design Engineer.