

ITEM - AGGREGATE BASE (Class 3)

The Aggregate Base shall be Class 3, and shall be as specified in Section 303 of the Standard Specifications. The grading shall be as follows:

Sieve Size	% Passing

The plasticity index shall not exceed ____.

The estimated haul distance for the Aggregate Base is miles.

DESIGNER:

This Item is used for AB Class 3. The gradation and plasticity index requirements shown below are typical for AB Class 3 and can be used as a guideline.

Sieve Size	% Passing
1"	100
3/4"	80 - 100
3/8"	55 - 75
#8	30 - 45
#200	0 - **

The plasticity index shall not exceed 3.

* To be supplied by the Geotechnical Site Supervisor.

** Information to be supplied by Geotechnical Services. Typically, 6.0% or 8.0% is used.

If the use of salvaged asphaltic concrete or Portland cement concrete is being considered for AB on a project, see Item # 303c.